An Electropolishing Primer

A user's guide to applications, quality standards and specifications . . .

Lectropolishing is used as a replacement for mechanical finishing, polishing, buffing and mass finishing. In addition to making a part's surface smoother, it is a more visible means of brightening, deburring, passivating, stress relieving and otherwise improving the physical characteristics of most metals and alloys.

History. The first reference to electropolishing was found in 1912, when the Imperial German government issued a patent for the finishing of silver in a cyanide solution.

Further experimentation continued, however, the next significant advancement was not made until 1935 when copper was successfully electropolished. Following this, stainless steel and other metals also were successfully electropolished. During World War II new formulas and results were developed. Dozens of new patents were registered between 1940 and 1955.

The Process. In electropolishing, metal is dissolved in an anodic film highly saturated with chemicals that dissolve basis metal at a current density allowing a steady transfer of solid (basis metal) into the adjacent film, as a metallic salt of the chemicals.

Because of the high voltage (six to 10 volts) and amperage (25 to 1,000 asf), microscopic high points (peaks) are selectively "deplated" faster than lower-current-density areas (valleys). Electropolishing is basically reverse plating, and, since high-current density areas on plated parts are characterized as burn areas, it follows that high-current-density areas dissolve faster in electropolishing.

Metal removal is controllable and can be held to 0.0001 to 0.0025 inch. After electropolishing, the metal surface is bright, clean and microscopically smooth.

The part's surface condition prior to electropolishing and process controls determines smoothness and reflectivity. Conditions that may result in a poor electropolished finish include improper annealing, over pickling, heat scale, large grain size, directional roll marks, insufficient cold reduction or excessive cold working. Because electropolishing removes metal, these flaws are exposed and more pronounced after processing. Process control determines the quality and consistency of the finish. Using the proper electrolyte is imperative. Temperature control and bath monitoring are also essential. Temperature should be maintained at 120F. This can be achieved by covering the tank when not in use. Critical chemistry factors are specific gravity, acid concentration and metal content. Clean, ripple-free DC current is needed to drive the process.

The real "art" of electropolishing lies with the operator who must configure a cathode for optimum polishing in inaccessible areas, corners and areas of low-current density. The operator must also know where, when and how to agitate either the electrolyte or the part to prevent gassing streaks, flow marks and other imperfections.

Heating and/or cooling coils in the tank are best located behind the cathode but care must be taken to allow good solution flow around and across the coil's surface. Stainless steel coils are best protected from stray current by having them hooked up to the source of cathode current at five asf. The bath. Many chemical combinations are used for electropolishing, depending on the basis metal. The most widely used are the sulfuricphosphoric acid combinations, with or without chromic acid. The chromic acid buffers the chemical attack and provides more latitude in subsequent rinsing after electropolishing.

For solutions not containing chromium, copper racks can be used. Titanium racks may be used if not connected to the cathode. For solutions that use chromium or its salts, contacts may be spring steel, copper plated or cold-worked copper. However, in either case, the contacts should be tin or tin-lead plated 0.00025- to 0.000-inch thick to prevent copper contamination of the bath.

Properly controlled electropolishing enriches the stainless steel surface with chromium. A consistent chromium-rich oxide layer is possible when the atomic concentration of chrome exceeds the iron in the surface layer. This is measured using an Auger Electron Spectroscopy (AES). AES analysis also measures depth and extent of surface passivation. Electropolishing maximizes surface passivation because the source contains low levels of iron in zero oxidation states.

Sulfide, precipitated carbides and other impurities are also measured using AES. The end grain surfaces of free-machining stainless grades such as Type 303 and 416 will appear frosty after electropolishing because sulfide is removed. Type 302 stainless steel will pit if the annealing process fails to re-dissolve the precipitated carbides.

Properties of Electropolished Surfaces

Surface Roughness. A profilometer measures surface roughness using Ra (roughness average) or Rq (equal to RMS, root mean square). Both are measured in microinches and denote the smoothness of ground or machined surfaces. However, the profilometer cannot accurately read the distance between the "peaks" and "valleys."

Electropolishing processes may reduce peaks from substantial points to insignificant mounds without changing the peak-to-peak distance at the same ratio. However, microscopic examination of the electropolished surface will show up to a 90 pct reduction in surface area and up to a 50 pct improvement in profilometer readings.

Friction Reduction. Electropolishing reduces the coefficient of friction of metals. The process removes or rounds off the small surface projections, yielding a coefficient of friction that measures approximately one-fourth of the coefficient restored by a mechanically finished surface.

Electropolished Castings. Various alloys are used in most castings, making them less suitable for electropolishing. The major exception is stainless steel.

Electropolished stainless steel castings will be brightened but will be neither as smooth as strip stock nor obtain the same mirror finish. The process decontaminates and passivates the metal surface, however, it may remove the surface of the casting, exposing sub-surface porosity.

Electropolishing cannot smear over or conceal defects such as seams and non-metallic inclusions in metals. Heavy orange peel, mold-surface texture and rough scratches are not removed and require an initial cut down with abrasives.

Applications. Electropolishing can be used on difficult and hard-tohandle parts and those with deep recesses. It is also good for applications where cathodes can be used and where individual processing become labor intensive. Specific applications include jet aircraft turbine compressor blades, bearing, smoothing heating coils, hypodermic needles, pipe, tubing, stampings, wire goods, valves, spinnings, forgings, fittings, fasteners, sheet metal, castings and drawings.

When used for storage tanks, reactor vessels, heat exchangers and agitators, it reduces part wear, reduces adhesion, contamination, corrosion and friction, while improving heattransfer efficiency. **Defects.** High quality electropolished parts should have a brilliant luster and reflectivity. The smoother the part surface, the higher the brilliance and reflectivity after electropolishing. Finished parts should be free from frosting, shadows, irregular patterns, streaks, water spots, pits, orange peel, erosion and a pebbly appearance. Under high magnification the surface should show no grain boundaries.

How to Specify Electropolishing

Step One. Specify the correct metal alloy. For example, a general materials specification to manufacture a part from 300 series stainless steel alloy can create problems. Some 300 steels are better to electropolish. Type 316 generally polishes better than 304. Type 303 has sulfide that may not allow for high-grade electropolishing.

Step Two. Use sample coupons to help determine the exact final finish. You may find you need an intermediate stop of mechanical abrasive polishing prior to electropolishing.

Step Three. Decide if any mechanical polishing will be required. Multiple passes of finer abrasive grits are recommended for best results. Coarse grits of less than 80 should be avoided. Electropolishing is directly related to the condition of the part prior to processing. Electropolishing does not remove digs, gouges, scratches or other distortions.

Recognizing a quality finish. High-quality electropolishing can usually be identified by visual inspection. A microscopic evaluation is necessary where a "maximum" finish is required and where the surface condition must be documented.

For example, a buffed surface often appears to be electropolished. Either finish yields the same surface finish profilometer readings. Only photomicrographs of the two surfaces would show the difference between the two surfaces. The electropolished surface would be featureless, while the buffed surface would show layers of smeared, disturbed and damaged metal, as well as embedded abrasive and buffing compound.

Electropolishing removes metal. It does not move it or wipe it. The surface of the metal is microscopically featureless, with no torn surface remaining. The basic surface of electropolished metal is bright and clean. **PF**

Abstracted from "*Electropolishing* — A User's *Guide*", with permission from Delstar, a division of Delaronde Corp., Austin, Texas.

More Information?

To obtain more information on products or processes mentioned in this article, circle corresponding numbers on the Reader Service Card.

Electropolishing Circle 281

To request an additional copy of this article, write on company letterhead to "Reprints," c/o PRODUCTS FINISHING, 6600 Clough Pike, Cincinnati, OH 45244.