

**UNCLASSIFIED**

---

**AD 272 099**

---

*Reproduced  
by the*

**ARMED SERVICES TECHNICAL INFORMATION AGENCY  
ARLINGTON HALL STATION  
ARLINGTON 12, VIRGINIA**



---

**UNCLASSIFIED**

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

REPORT NO: FGT-2407  
DATE: 16 January 1962

62-2-3  
NOX

PROCESSING - PLATING SYSTEMS - UNCLAD 2020  
ALUMINUM ALLOY - CHEMICAL AND PHYSICAL  
PROPERTIES - EVALUATION OF

Published and Distributed Under  
Contract No. AF33(657)-7248

351860

GENERAL DYNAMICS | FORT WORTH

**Best  
Available  
Copy**

<i>m</i>	NO.	DATE	BY	CHANGE	PAGES AFFECTED
npe					

PROCESSING - PLATING SYSTEMS - UNCLAD 2020 ALUMINUM ALLOY--  
CHEMICAL AND PHYSICAL PROPERTIES - EVALUATION OF -

PURPOSE:

The use of X-2020 aluminum, a new alloy possessing a high strength to weight ratio at elevated temperatures, is being considered for applications on the B-58. Through its use, an appreciable weight saving over conventional aluminum alloys might be realized.

One of the criteria in the selection of this material is its electroplating characteristics and electroplated properties. The purpose of this test was to evaluate the plating methods and plate properties of various plating systems for unclad X-2020 aluminum alloy exposed to elevated and room temperature heat soak treatments.

SUMMARY:

Specimens of X-2020 aluminum alloy were plated by procedures employing (1) no pretreatment of basis metal and (2) sodium zincate pretreatment of basis metal. The specimens were plated with chromium and tin by standard electrolytic methods and with electroless nickel by the Alkaline type, modified Hydrac type, and Dow Process type baths. Plated specimens were then exposed to 100 hour heat soak performance tests at temperatures up to 350°F and subsequently evaluated for plating adhesion and corrosion resistance.

Two general classes of specimens were prepared: (1) coupon type for tape stripping and bend adhesion tests and for salt spray corrosion tests, and (2) galvanic specimens for use in three phase JP-4-- salt water immersion tests. The galvanic specimens consisted of plated X-2020 aluminum coupled to coated HK-31 magnesium by procedures specified in FPS-0060.

Visual observations and tape stripping test results revealed that the platings applied to X-2020 aluminum by the direct method (no pretreatment) exhibited extremely poor adhesion. Therefore, the direct plated specimens were not evaluated further.

# CONVAIR

A DIVISION OF GENERAL DYNAMICS CORPORATION  
(FORT WORTH)

PAGE 2  
REPORT NO. FGT-2407  
MODEL B-58  
DATE 4-12-60

## SUMMARY: (continued)

The results of bend and tape stripping tests indicate acceptable adhesion for specimens prepared by all plating procedures employing the zincate pretreatment. No detrimental effects in adhesion were noted as the result of the elevated temperature heat soak performance tests.

The salt spray corrosion resistance was within the respective specification requirements for all platings employing zincate pretreatment with the exception of those of chromium and tin exposed to the 350°F heat soak.

All galvanic corrosion test specimens exposed to three phase immersion failed within 48 hours except those incorporating tin plated components that were held at room temperature.

PROCESSING - PLATING SYSTEMS - UNCLAD 2020 ALUMINUM ALLOY -  
CHEMICAL AND PHYSICAL PROPERTIES - EVALUATION OF -

OBJECT:

- (1) To establish methods for plating tin, chromium, and Alkaline Type, Hydrac, and Dow process electroless nickel on X-2020 aluminum.
- (2) To evaluate the adhesion and corrosion resistance of the above plates on X-2020 aluminum after exposure to room and elevated temperatures.

TEST SPECIMENS, MATERIALS, AND EQUIPMENT:

A detailed list of the test specimens, materials, and equipment used during this test is given in Table I. Test specimens for plate adhesion and salt spray corrosion tests were 1" x 5" x .040" coupons of bare X-2020 aluminum alloy. Galvanic corrosion specimens were formed by coupling similar coupons (plated) to Dow "17" treated and painted HK-31 magnesium components which were 4" x 5" x 0.064" in size. Countersunk holes for AN-426B-4-5 rivets used for joining specimens were placed 1/4" from each end along the centerline of the components.

PROCEDURE:

An outline of test procedures, including plating methods and heat soak performance tests applicable to individual specimens are called out in Table II. Detailed procedures for pretreatments, plating, Dow "17", and paint coating operations are presented in Table III.

RESULTS:

The results of bend and tape stripping tests indicated acceptable adhesion for all specimens prepared by all plating procedures employing the zincate pretreatment method. No detrimental effects in adhesion were noted as the result of elevated temperature heat soak performance tests. Direct plating methods failed to produce the desired physical properties.



## RESULTS: (continued)

The results of salt spray corrosion tests are presented in Table IV. Three phase corrosion tests on galvanic specimens are given in Table V.

## DISCUSSION:

In view of the good results previously obtained for alkaline type electroless nickel on 7075-T6 aluminum as given in FGT-2106 (Determination of corrosion resistance of electroless nickel plated bare 7075-T6 aluminum) this process was also evaluated on X-2020 aluminum. The low Hydrac bath, also evaluated in the above test, required a similar modification (use of sulfate salts instead of the more active chloride) as reported therein. The unmodified bath reacted strongly with both 7075-T6 and X-2020 aluminum alloys, thereby preventing the formation of plates.

The direct plating pretreatment method as presented in the procedure section was not systematically evaluated because of the poor results observed during or after the plating operation such as spontaneous peeling of electrolytic (chromium, tin) plates, and removal of electroless nickel plates by tape stripping.

Results of 250 hours salt spray on plated X-2020 aluminum previously exposed to 350°F, 300°F, and room temperature are shown in Figures 1 through 5. These photographs show the general decrease in performance of chromium and tin with increasing heat soak temperature. Specimens exposed to 350°F failed salt spray within 24 hours. Comparison of 350°F results with those obtained at 300°F indicates a rather critical temperature vs. corrosion resistance transition point, thereby limiting the use of these plates on X-2020 to temperatures not above 300°F. Electroless nickel plates were not adversely affected by elevated temperatures.

Figure 6 shows the configuration of galvanic specimens and the typical results obtained after exposure to 48 hours in 3 phase (3% salt solution - JP-4 fuel - JP-4 vapor) corrosion environment.

One hundred hour exposure, as requested, was not completed due to the heavy attack noted after 48 hours. Specimen No. 8 of Figure 6 demonstrates the acceptable resistance offered by specimens incorporating tin plates which were held at room temperature. No definite variation in corrosion effects for different heat soak temperatures was noted for electroless

DISCUSSION: (Continued)

nickel, and the degree of corrosion was seen to be parallel to (but greater than) salt spray results.

Plating evaluations on X-2020 material were commensurate with the characteristics and behavior expected of more conventional aluminum alloys. Electrolytic processes on X-2020 required the zincate pretreatment, followed by deposition of a copper plate of approximately 0.0001" in thickness. This thickness of copper plate served to prevent penetration of active solutions through pores to the basis metal, causing a corrosive reaction and subsequent pitting or poor adhesion.

Electroless nickel baths, from considerations including stability (tendency toward spontaneous decomposition), ease of constituent control, plating rate, and plating appearance fall into a decreasing order of preference as follows:

(1) Alkaline type, (2) Dow Process, (3) Modified Hydrac. When considered from a standpoint of plate characteristics, i.e. adhesion to basis metal and corrosion protection, they fall into the following decreasing order: (1) Alkaline Type, (2) Modified Hydrac, (3) Dow process.

CONCLUSIONS:

(1) Adherent and attractive plates of chromium, tin, Dow's electroless, Modified Hydrac, and Alkaline Type electroless nickel were produced on X-2020 aluminum by all procedures employing the zincate pretreatment.

(2) Salt spray corrosion resistance passed specification requirements for all plates with exception of electrolytic methods (tin and chromium) on specimens that were exposed to the 350°F heat soak performance tests. Performance of chromium and tin were closely parallel at varied temperature exposures. Alkaline type electroless nickel was found to be superior to other procedures evaluated.

(3) All galvanic corrosion specimens failed 3-phase immersion testing after 48 hours exposure with exception of the group incorporating tin plates held at room temperature.

TABLE I

TEST SPECIMENS, MATERIALS, AND EQUIPMENT

I. TEST SPECIMENS:

<u>Item</u>	<u>Quantity</u>	<u>Source</u>
Plating specimens .040" x 1" x 5" X-2020 Aluminum alloy	210	Dow Chemical Co. Midland, Michigan
HK-31-H 24 Magnesium-Thorium Alloy (FMS-0046) .064" x 4" x 5"	48	Dow Chemical Co. Midland, Michigan
5056 Aluminum rivet (AN 426B-4-5)	96	Convair Stock

II. MATERIALS:

Zincate immersion pretreatment solution	Prepared in Chemistry Laboratory (See Table III for details)
Copper strike plating solution ✓	"
Rochelle copper plating solution ✓	"
Stannate tin plating solution ✓	"
Watt's nickel plating solution ✓	"
Chromium plating solution ✓	"
Dow Process electroless nickel (proprietary formulation) ✓	"
Hydrac electroless nickel	"
Alkaline type electroless nickel ✓	"
Dow "17" treatment solution ✓	"
D.C. XP-214 silicone primer ✓	NAPCO Paint Co., Houston, Texas

# CONVAIR

A DIVISION OF GENERAL DYNAMICS CORPORATION  
(FORT WORTH)

PAGE 7  
REPORT NO. FGT-2407  
MODEL B-58  
DATE 4-12-60

- TABLE I  
(continued)

## TEST SPECIMENS, MATERIALS, AND EQUIPMENT

### III. EQUIPMENT:

<u>Item</u>	<u>Source</u>
0-350°F Oven	Blue "M" Electric Co., Blue Island, Ill.
Salt Spray Chamber	Industrial Filter & Pump Mfg. Company, Chicago, Ill.
Electroplating test fixture	Convair built
Vapor degreaser	Convair built
Bend tester	O'Neil-Irwin Mfg. Co. Lake City, Minn.
Dermatron thickness tester	Unit Process Assemblies Inc., New York 3, N. Y.

# CONVAIR

A DIVISION OF GENERAL DYNAMICS CORPORATION  
(FORT WORTH)

PAGE 8  
REPORT NO. FGT-2407  
MODEL B-58  
DATE 4-12-60

## TABLE II

OUTLINE OF SPECIMEN PREPARATION AND TESTING DESIGNATIONS

PLATING SYSTEM	PRE-TEST HEAT SOAK	TYPE OF TEST			
		JP-4 SALT SOAK CORROSION	TAPE STRIPPING	BEND TEST	SALT SPRAY
A. .0001" COPPER .0002" NICKEL .0005" CHROMIUM	#				
	1	Room Temp	49-50	51-52	53-54
	2	100 HRS-300°F	55-56	57-58	59-60
B. .0001" COPPER .0005" TIN	3	100 HRS-350°F	61-62	63-64	65-66
	1	Room Temp	67-68	69-70	71-72
	2	100 HRS-300°F	73-74	75-76	77-78
C. DOW ELECTROLESS NICKEL .001"	3	100 HRS-350°F	79-80	81-82	83-84
	1	Room Temp	85-86	87-88	89-90
	2	100 HRS-300°F	91-92	93-94	95-96
D. MODIFIED HYDRAC ELECTROLESS NICKEL .001"	3	100 HRS-350°F	97-98	99-100	101-102
	1	Room Temp	103-104	105-106	107-108
	2	100 HRS-300°F	109-110	111-112	113-114
E. ALKALINE TYPE ELECTROLESS NICKEL .001"	3	100 HRS-350°F	115-116	117-118	119-120
	1	Room Temp	193-194	195-196	197-198
	2	100 HRS-300°F	199-200	201-202	203-204
	3	100 HRS-350°F	205-206	207-208	209-210

SPECIMENS # 25 THRU 48, 121 THRU 192 WERE USED FOR DIRECT PLATING EVALUATIONS

TABLE IIISPECIMEN PREPARATION AND TEST PROCEDURESI. Pre-Plating Surface Treatments For X-2020 Aluminum:

- A. Perform standard cleaning operation with methyl ethyl ketone followed by vapor degreasing in trichloroethylene.
- B. Immerse for 1-2 minutes in 50% by volume nitric acid at 160-180°F to remove additional surface contaminants.
- C. Tap water rinse
- D. Etch for 2-3 minutes or until surface attains uniform appearance (black) in a solution of 20 oz/gallon sodium hydroxide held at room temperature.
- E. Tap water rinse
- F. Immerse at room temperature in 50% by volume nitric acid for 30-60 seconds as necessary to remove residue from operation D.
- G. Tap water rinse
- H. 1. Perform double zincate treatment for specimen so designated.
  - a. Using 2S aluminum wire suspension, immerse for 60 seconds in a solution of 70 oz/gal sodium hydroxide and 12 oz/gal zinc oxide held at room temperature. Agitate part mildly.
  - b. Tap water rinse
  - c. Remove zinc film by 30 seconds immersion in 50% by volume nitric acid at room temperature.
  - d. Tap water rinse
  - e. Repeat step "a"
  - f. Tap water rinse and perform succeeding plating operation immediately.

TABLE III  
(continued)

SPECIMEN PREPARATION AND TEST PROCEDURES

I. H. (continued)

2. Specimens designated for direct plating were processed by steps IA through IG only, then immersed for 1 minute in 5% by volume hydrochloric acid for activation, rinsed, and plated.

II. Procedure for Application of Plates On X-2020 Aluminum Alloy By Electrolytic Processes.

A. Copper strike

Composition

Copper Cyanide	2.0 oz/gal
Sodium Cyanide	3.0 oz/gal
Caustic Soda	0.25 - 0.50 oz/gal

Operating Conditions

Temperature	120°F
Anodes	Stainless Steel
Potential (volts D.C.)	6
Immerse with potential applied to part.	

B. Tap water rinse

C. Copper Plate to 0.0001" thickness

Composition:

Copper Cyanide	3.5 oz/gal
Sodium Cyanide	4.6 oz/gal
Sodium Carbonate	4.0 oz/gal
Potassium Sodium Tartrate	6.0 oz/gal
Free Sodium Cyanide	0.75 oz/gal
Sodium Hydroxide	To pH 12.6
Anodes	Pure electrolytic copper

Operating Conditions:

Temperature	130°F
Current Density	30 amps/Ft. <sup>2</sup>

TABLE III  
(continued)

SPECIMEN PREPARATION AND TEST PROCEDURES

II. (continued)

D. Tap water rinse

E. Application of Nickel and Chromium on System "A" Specimens, Table II.

1. Nickel Plate 0.0002" thickness

Composition

Nickel Sulfate	32 oz/gal
Nickel Chloride	6 oz/gal
Boric Acid	4 oz/gal
Anodes	pure nickel

Operating Conditions:

Temperature	140°F
Current Density	40 amps/Ft <sup>2</sup>
pH	4.5

2. Chromium Plate 0.0005" Thickness

Composition:

Chromic Acid	53 oz/gal
Sulfate Ion (as sulfuric acid)	0.53 oz/gal
Anodes	Lead alloy

Operating Conditions:

Temperature	130-140°F
Current Density	2 amps/in <sup>2</sup>

F. Application Of Tin (0.0005") on System "B" Specimens, Table II.

Proceed immediately from operation D to the stannate tin plating solution:

Composition:

Sodium Stannate	14 oz/gal
Sodium Hydroxide	1.25 oz/gal
Tin metal	5.6 oz/gal
Anodes	pure tin (filmed)



TABLE III  
(continued)

SPECIMEN PREPARATION AND TEST PROCEDURES

II. F. (continued)

Operating Conditions:

Cathodic Current Density (D.C.)	30 amps/Ft <sup>2</sup>
Anodic Current Density	15 amps/Ft <sup>2</sup>
Temperature	150 plus/minus 5°F.

III. Procedures For Application Of Plates On X-2020 Aluminum By Electroless Processes Designated As Plating Systems C, D, and E on Table II

A. System "C" - Dow Electroless Nickel - 0.001" Thickness.  
Composition and Operating Conditions: Proprietary data of Dow Chemical Corporation not to be published in Convair Reports.

B. System "D" - Hydrac Electroless Nickel - 0.001" Thickness.  
Composition and Operating Conditions:

Nickel Sulfate	4 oz/gal
Sodium Hypophosphite	1.3 oz/gal
Hydroxyacetic (glycolic) acid	3.0 oz/gal
Sodium Hydroxide	for pH adjustment
pH	4.0-4.3
Temperature	203-212°F

C. System "E" Alkaline Type Electroless Nickel - 0.001" Thickness.  
Composition and Operating Conditions:

Nickel Chloride Solution (80 oz/gal)	4.0 fl oz/gal
Ammonium Hydroxide	to pH 8-10
Sodium Hypophosphite	1.0 oz/gal.
Ammonium Chloride	6.5 oz/gal
Sodium Citrate	9.5 oz/gal
Temperature	195-205°F

IV. Passivation of Plates:

System "B" - Immerse in 0.25% by weight chromic acid at 180°F for 30 seconds.

Systems "C - E" - Immerse as above for a period of 10 minutes.

TABLE III  
(continued)

SPECIMEN PREPARATION AND TEST PROCEDURES

V. Preparation of Galvanic Corrosion Test Specimens

A. HK-31 Magnesium Components:

1. Clean and degrease according to standard procedures stated in Section I of this Table.
2. Apply a Dow "17" coating as specified in FPS-0045 to a thickness of .0003".

Composition:

Ammonium acid Fluoride	32 oz/gal
Sodium Dichromate	13.3 oz/gal
Phosphoric acid 85%	11.5 fl oz/gal

Operating Conditions:

Current Density (amps/Ft <sup>2</sup> )	5 - 50
Temperature	160-180°F
Potential (A.C.)	110 volts

3. Apply D.C. XP-214 silicone base primer to thickness of .35 plus or minus .05 mils.
4. Air dry for 30 minutes, then bake at 350°F for 30 minutes.
5. Sand lightly with No. 400 "wet or dry" sandpaper to remove protrusions.
6. Apply second coating of XP-214 primer as specified.
7. Repeat step 4.

B. Plated X-2020 Aluminum Components: Preparation procedures previously specified in this table.

C. Joining of Aluminum and Magnesium Components;

Specimens were joined with AN 426B-4-5 rivets by procedures specified in FPS-0060, Corrosion Protection and Finishing of Magnesium - Thorium and Dissimilar Metals.

TABLE III  
(continued)

SPECIMEN PREPARATION AND TEST PROCEDURES

VI. Pre-test Heat Soak: Specimens to be subjected to 100 hours heat soak at 350°F, 300°F, and those to be held at room temperature are specified in Table II.

VII. Evaluation of Specimens:

A. Tape Stripping Adhesion Test: Pressure sensitive tape 3M No. 250 was applied uniformly to the plated specimens designated in Table II. Adhesion testing, was accomplished by removal of tape with one abrupt motion, followed by examination of the tape and specimen for evidence of plate adhesion failure.

B. Bend Test For Plate Adhesion: Specimens were bent through an angle of 180° on a 1/4" diameter until fracture of the basis metal occurred. Visual examination at the stressed and fractured area was made for non-adhesion of plate to determine failure.

C. Salt Spray Porosity Test: The required specimens were subjected to salt spray exposure for 250 hours in accordance with Federal Test Method Standard No. 151, Method. 811. Inspection for excessive corrosion (as specified below) was performed at 24 hour increments.

Plate	Specification	Extent Required For Failure
Chromium on Aluminum	FPS-0028	"excessive" corrosion after 48 hours
Tin on Aluminum	FPS-0029	1 pit/in. <sup>2</sup> after 48 hours
Electroless Nickel on Aluminum	FPS-0017	No corrosion after 48 hours.

D. 3-Phase Corrosion Test: Galvanic corrosion specimens were immersed in a corrosion inducing media of 3% sodium chloride, JP-4 fuel, and JP-4 vapors held at 140°F for 48 hours. Visible breaks in coatings and corrosive attack in any phase constituted failure.

# CONVAIR

A DIVISION OF GENERAL DYNAMICS CORPORATION  
(FORT WORTH)

PAGE 15  
REPORT NO. FGT-2407  
MODEL B-58  
DATE 4-12-60

TABLE IV  
EFFECTS OF 250 HOUR SALT SPRAY ON PLATED X-2020 ALUMINUM

TYPE OF PLATES APPLIED	PRE-TEST ENVIRONMENT		SPECIMEN NUMBER	HOURS EXPOSED TO SALT SPRAY										CONCLUSIONS
	#			24	48	96	120	144	168	192	216	250		
.0001" COPPER .0002" NICKEL .0005" CHROMIUM	1	ROOM	53											PASS
		TEMP	54											PASS
	2	100 HRS	59											FAIL
		300°F	60											FAIL
	3	100 HRS	65											FAIL
		350°F	66											FAIL
.0001" COPPER .0005" TIN	1	ROOM	71											PASS
		TEMP	72											PASS
	2	100 HRS	77											FAIL
		300°F	78											FAIL
	3	100 HRS	83											FAIL
		350°F	84											FAIL
DOW ELECTROLESS NICKEL .001"	1	ROOM	89											FAIL
		TEMP	90											FAIL
	2	100 HRS	95											FAIL
		300°F	96											FAIL
	3	100 HRS	101											FAIL
		350°F	102											FAIL
MODIFIED HYDRAL ELECTROLESS NICKEL .001"	1	ROOM	107											PASS
		TEMP	108											FAIL
	2	100 HRS	113											FAIL
		300°F	114											FAIL
	3	100 HRS	119											FAIL
		350°F	120											FAIL
ALKALINE TYPE ELECTROLESS NICKEL .001"	1	ROOM	197											FAIL
		TEMP	198											FAIL
	2	100 HRS	203											PASS
		300°F	204											FAIL
	3	100 HRS	209											PASS
		350°F	210											PASS

TABLE V

RESULTS OF 48 HOUR 3-PHASE IMMERSION TEST ON GALVANIC CORROSION SPECIMENS

TYPE OF PLATE APPLIED COMPONENT	SPECIMEN NUMBER AND HEAT SOAK	TYPE OF CORROSION							CORROSION APPEARANCE AT FAYING EDGES	C.L.C.
		X-2020 ALUMINUM COMPONENT					H.C. 31 MAG. COMPONENT			
		PITS	BUSTERS	FLACING, LOSS OF PLATE	FAYING EDGES	GENERAL APPEARANCE (CORROSION)				
COPPER .0001" NICKEL .0002" ALUMINUM .0005" "CONSECUTIVE LAYERS"	1 Room	Small-Numerous	NONE	EDGE AND END	SLIGHT	RIVET AREA	HEAVY	FAI		
	2 TEMP	NONE	"	NONE	"	EDGE AND RIVET AREA	"	"		
	3 300°F	ONE AREA ONLY	"	"	"	"	"	"		
	4 100 HRS	SLIGHT	"	"	"	"	SLIGHT	"		
	5 350°F	NUMEROUS	"	"	"	"	"	"		
	6 100 HRS	Small-Numerous	"	"	NONE	NONE	NONE	"		
COPPER .0001" TIN .0005" "CONSECUTIVE LAYERS"	7 Room	NONE	NONE	NONE	SLIGHT	NONE	"	PASS		
	8 TEMP	"	"	"	NONE	"	"	"		
	9 300°F	"	"	"	"	RIVET AREA	"	FAIL		
	10 100 HRS	"	"	"	"	END AND RIVET AREA	SLIGHT	"		
	11 350°F	"	Small-Numerous	"	"	RIVET AREA	HEAVY	"		
	12 100 HRS	Small-Numerous	Small-Numerous	"	SLIGHT	2 HOLES, SLIGHT EDGE ATTACK	HEAVY	"		
LOW ELECTROLESS NICKEL .001"	13 Room	NONE	HEAVY	HEAVY	HEAVY	HEAVY	"	FAI		
	14 TEMP	"	"	HEAVY	NONE	"	" ON END	"		
	15 300°F	"	"	SLIGHT	SLIGHT	HEAVY EDGE CORROSION	SLIGHT	"		
	16 100 HRS	"	"	SLIGHT	SLIGHT	" ON END	HEAVY ON END	"		
	17 350°F	1	"	HEAVY	HEAVY	" ON ONE EDGE	HEAVY	"		
	18 100 HRS	2	SLIGHT	HEAVY	HEAVY	" ON BOTH HOLES IN BASE	"	"		
MODIFIED HYDRAC ELECTROLESS NICKEL .001"	19 Room	NONE	HEAVY	NONE	NONE	NONE	SLIGHT - 1 AT	FAI		
	20 TEMP	"	MEDIUM	"	"	TWO HOLES	"	"		
	21 300°F	"	SLIGHT	"	"	RIVET AREA	" 2"	"		
	22 100 HRS	"	SLIGHT	"	SLIGHT	5 HOLES	MED	"		
	23 350°F	"	SLIGHT	"	"	HOLES + HEAVY ON EDGE	HEAVY	"		
	24 100 HRS	"	HEAVY	"	"	4 HOLES, EDGE CORROSION	HEAVY	"		




# CONVAIR


A DIVISION OF GENERAL DYNAMICS CORPORATION  
(FORT WORTH)

PAGE 17  
REPORT NO. FGT-2407  
MODEL B-58  
DATE 4-12-60

TABLE VI  
PHOTOGRAPHIC INDEX

<u>FIGURE NUMBER</u>	<u>TITLE</u>	<u>NEGATIVE NUMBER</u>
1	Effects of 250 Hours Salt Spray on Heat Soaked Chromium Plated X-2020 Aluminum Alloy	2-24167
2	Effects of 250 Hours Salt Spray on Heat Soaked Tin Plated X-2020 Aluminum Alloy	2-24168
3	Effects of 250 Hours Salt Spray on Dow Electroless Nickel Plated X-2020 Aluminum Alloy	2-24170
4	Effects of 250 Hours Salt Spray on Modified Hydrac Electroless Nickel Plated X-2020 Aluminum Alloy	2-24169
5	Effects of 250 Hours Salt Spray on Alkaline Type Electroless Nickel Plated X-2020 Aluminum Alloy	2-24171
6.	X-2020 Aluminum to HK-31 Magnesium Galvanic Corrosion Specimens Exposed to 48 Hours 3-Phase Immersion	2-24172

















FIGURE 6  
X-2020 aluminum, HF-31  
magnesium galvanic  
corrosion specimens  
exposed to 48 hours  
3 phase immersion test